

SPECIFICATION- MASONRY BLOCK STANDARD

Application of render and textured finish to concrete blockwork. (Applies to unpainted concrete blockwork constructions)

Warranty

7 or 10 years from time of application. See notes.

When applied in accordance with the above specification, Chase will provide a 7 or 10 year materials warranty against peeling and delamination. This warranty does not cover workmanship or product failure caused as a result of hydrostatic pressure, entrapped moisture or structural/substrate/joint movement.

See warranty for details.

Substrate Preparation General

Substrate/base boards/panels should be installed in strict accordance with substrate manufacturer's technical documentation. Acrylic paints, primers, and textured finishes not to be applied to any substrate with a moisture content of greater than 10% wood moisture equivalent (WME), or with an alkalinity reading (pH) of greater than 10. Ensure sufficient curing period for cement-based surfaces has been reached.

All surfaces must be clean and free from any impurities which may adversely affect the bond strength of primers, renders and applied finishes.

All horizontal surfaces such as, fence caps and windowsills must be installed with a minimum 10 degree fall to facilitate drainage of water and eliminate ponding.

Ensure all capping and weatherproofing has been installed to ensure moisture cannot attack the finished coating from within the wall system and ensure all down pipes are reconnected after render/coating application.

Substrate Preparation Specific

Fill any holes and repair imperfections in with any of Chase's standard grade renders such as Chase GP Render Coarse

Allow repaired sections to dry fully before application of textured finish

Control Joints

Control/movement joints must be positioned and detailed as per substrate manufacturer's recommendation.

Control/movement joints must not be bridged by the base coat or finish coat system.

Unless otherwise specified by substrate manufacturer or consulting engineer, Chase requires the placement of control/movement joints at 5 metre (maximum) centres and at stress points such as in line with openings (window / doors), at all horizontal multi-levels, and at all interfaces of non-identical building construction materials.

CHASE

Basecoat - Fibre Reinforced

Refer to product data sheet prior to use.

Mechanically mix Chase GP Render Coarse powder with approximately 3 - 4 litres of potable water. Allow to stand for 2 minutes then re-blend prior to application.

Apply Chase GP Render Coarse with a trowel or angled 6 mm notched trowel. Overlay with fibreglass mesh and work lightly into the wet render ensuring surface is fully covered. Ensure mesh is sitting near the render surface, not close to the substrate surface.

Overlap fibreglass mesh junctures by 100 mm minimum. Ensure render surface finish is suitable for the application of a second coat of render.

Corners at openings including window and door frames must be diagonally reinforced with 400 mm x 200 mm fibreglass bandages embedded in the first Chase GP Render Coarse coat. This is in addition to the full fibreglass mesh embedded in the first render coat.

Basecoat

Refer to product data sheet prior to application.

Mix render with potable water (or Macbond gauging solution if required) as directed and apply evenly with trowel at a thickness between 3 - 6 mm.

Allow to firm up sufficiently prior to floating to a level surface using a plastic render float. Ensure suitable finish has been achieved for successful application of selected coating.

If second render coat is being applied over a basecoat of Chase EPS, mix using a Macbond:water ratio of 1:14.

Allow to dry for a minimum 4 days prior to application of a textured finish or membrane.

Priming

Apply with brush, roller or suitable spray equipment to all unsealed surfaces prior to application of base render. Allow primer to dry to a non-tack finish prior to over-coating.

Not required where surface is factory pre-primed with a compatible product. Check with a manufacturer for details.

Do not thin this product prior to application.

Textured Finish

Refer to product data sheet prior to application.

Prior to selection of colour, check this document thoroughly for mention of LRV restrictions (i.e. application of dark colours).

Apply selected trowel-on or roll-on textured finish in selected colour as per product specific product data sheet. Allow to dry for a minimum 24 hours prior to painting.

Hard dry may take longer than 24 hours under extremely damp, moist, or humid conditions

CHASE

Membrane

Refer to product data sheet prior to application.

Prior to selection of colour, check this document thoroughly for mention of LRV restrictions (i.e. application of dark colours).

With roller or suitable spray equipment, apply two coats of Chase Satin Flex 100% acrylic membrane in selected colour.

Cutting-in prior to coating application may result in "picture framing". Always cut in just ahead of or during main application, maintaining a "wet-edge" at all times.

Two (2) coats required. 7 year warranty applicable for Satin with 10 year warranty applicable for Satin Flex.

Disclaimer

Chase, its staff and distributors will not accept responsibility for any failure caused as a result of factors beyond our control including but not limited to onsite handling, preparation or application of this product.

Application of this product should only be performed by qualified trades people trained in the use of this type of product. Information supplied in this publication is based on our testing and experience and is given in good faith.

Where used outside of the scope detailed above, suitability of this product should be independently determined prior to use.

Chase will not warrant job defects caused as a result of but not limited to, structural/substrate movement or entrapped moisture. Building movement and structural dynamics is beyond the scope and control of Chase. Accordingly, stresses and joint/substrate movement cannot be contained by the application of the decorative finished detailed in the above specification.

In some circumstances, surface undulations, joints and panel deformation may be visible under glancing light conditions. This will result in the sun casting visible shadows over the joints in the wall. These imperfections may be extremely difficult to detect during application or at all other times. Glancing light occurs at certain times of the day when the sun's rays are nearly parallel to the surface. This will cause the casting of long and exaggerated shadows across the wall surface, most evident across taped or reinforced joints. As hand applied finishes are always susceptible to the minor undulations which cause these effects, glancing light issues are outside the control and/or scope of this specification.

Chase shall not be liable for surface staining, degradation or loss of adhesion resulting from contact with moisture from behind the face of the finished coating. Ensure capping's and downpipes are installed/replaced immediately after the application of the render/coating.

Colour change is a natural part of the weathering of applied finishes and is excluded from warranty terms.

Sufficient quantity of texture coating or paint/membrane required to complete a project must be purchased in a single order to minimise the risk of colour and or texture inconsistency. Always cross-batch drums on site prior to application to optimise colour/texture uniformity